











Quick-Finder – Cold Mounting

Reference	Type	Colour	Specifications	Components	Mixing ratio	Curing time at 25°C	Top T°	Shrinkage
DEMOTEC 10	Acrylic		white, and limited shrinkage	Powder / liquid / liquid	4P : 2L : 1L	13 min.	85°C	****
DEMOTEC 15+	Acrylic		gap free embedding by expansion, very hard	Powder/liquid	2P : 1L	12 min	85°C	*****
DEMOTEC 20	Acrylic		translucent or clear under pressure	Powder/liquid	2P : 1L	10 min.	84°C	**
DEMOTEC 30	Acrylic		green translucent	Powder/liquid	2P : 1L	10 min	78°C	**
DEMOTEC 33	Acrylic		soluble in acetone	Powder/liquid	2P : 1L	10 min	88°C	***
DEMOTEC 35	Acrylic		very hard and resistant	Powder/liquid	2P : 1L	8 min	80°C	***
DEMOTEC 70	Acrylic		electrically conductive	Powder/liquid	1P : 1L	18 min	105°C	**
XF40+XH40	Epoxy		very clear, top quality	Liquid/liquid	12%	8 to 12 hours	45°C	****
XF40+XH45	Epoxy		very clear, top quality	Liquid/liquid	26%	30 min. at 80°C	200°C	****
XF60	Polyester		non expensive	Liquid/liquid	2%	120 min.	75°C	*